



Recommendations	
Product Overview	
Product Code	EL9755
Industry	Inks
Application	Screen Printing
Category	White Inks
Chemistry	Plastisol
Substrate(s)	Poly
Best Used By	12 months
Certification(s)	ISO9001
Curing:	
Fusion Temperature	280 °F
Gel Point	150 °F
Performance:	
Coverage	High Opacity
After Flash Tack	Medium
Bleed Resistance	Great for 100% Polyester
Squeegee:	
Squeegee Profile	Square
Screen:	
Mesh	86 to 156
Underlay	EL0755 Endurance Plus Grey Base
Emulsion Type	Capillary film, Direct
Cleanup	Non-Phthalate screen wash
Storage:	
Storage Temperature	65°F - 95°F (18°C - 35°C)
Storage Notes	Avoid direct sun.

Last Change: Mar 2017

ENDURANCE PLUS WHITE

EL9755 Endurance Plus White is a press-ready non-phthalate white plastisol ink with great bleed resistance and a wide cure temperature range for printing on 100% Polyester Performance fabrics. For fabrics with severe migration, use EL0755 Endurance Plus Barrier Grey as an underlay. Endurance Plus White and Endurance Plus Barrier Grey have a cure temperature range from 280°F (138°C) to 300° F (149°C) while still blocking dye migration on most 100% Polyester fabrics. EL0209 Endurance Plus Mixing Base can be used with Rutland's C3 Color Boosters to create desired low temperature colors. Formulations are available in the RGCC Color Mixing software. Mixed colors would be printed over the Barrier Grey/White layer for the most brilliant prints. EL8209 Endurance Plus Black is also available with same low temperature print qualities. Great stretch and recovery makes it a perfect athletic ink. Complies as a non-phthalate and no lead product as defined by CPSC.

Features

- Low temperature cure from 280°F (138°C) to 300° F (149°C).
- Excellent bleed resistance for printing on 100% polyester performance fabrics.
- Smooth athletic surface on cured print.
- Soft drape, supple feel to the print.
- Great stretch and recovery makes it a perfect athletic ink
- Complies as a non-phthalate and no lead product as defined by CPSC.

Instructions

Print EL9755 Endurance Plus white over EL0755 Endurance Plus Barrier Grey or directly onto 100% Polyester substrates where applicable. NOTE: Poorly dyed polyester or too much heat in the curing process can overcome any low bleed inks ability to block dye migration. For severe migration use EL0755 Endurance Plus Barrier Grey as an underlay. Printers should always test the ink on their fabric under their process conditions before printing production runs.

Recommendation

Do not dry clean, bleach, or iron the printed image.

Statement

Rutland Plastic Technologies does not knowingly add plasticizers containing the phthalates listed and outlined in California Bill 1108, CPSIA HR-4040 and Oeko-tex Standard 100. The plasticizers identified may include di-(2-ethylhexyl) phthalate (DEHP), dibutyl phthalate (DBP), benzyl butyl phthalate (BBP), diisononyl phthalate (DINP), diisodecyl phthalate (DIDP), di-n-octyl phthalate (DnOP), (DIBP) Di-isobutyl, and (DMP) Dimethylphthalate, including esters of ortho-phthalic acid and are not direct ingredients in the manufacture of Clair High Opacity Non-Phthalate Inks. Rutland Plastic Technologies does not test the final product for amounts of the aforementioned phthalate plasticizers and esters and encourages all users to conduct testing for their intended use.

Disclaimer:

Not all Rutland products are available in every country. Please check with your local representative for availability. The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.